



BAKHTI Software Ltd

Civil engineering software development

Website: <https://www.bakhtisoftware.com>

Email: bakhti@bakhtisoftware.com / support@bakhtisoftware.com

Project: Suivi RN 18

Project No.: Ref 008/2020

Client: DTP

Location: Medea

Date: 2020-03-16

MICRO - DEVAL ABRASION TEST

Standard: NF P18-572 / NF EN 1097-1

Test: Micro-Deval N=1

Sample mass: 500 g

Testing type: With water

Granular class	Abrasive load (g)	Dry mass of sieve retained (g)	Dry mass of passing (g)	% loss	% loss (Average)
10/14	5000	376,00	124,00	24,80	24,78
		376,50	123,50	24,70	
		375,80	124,20	24,84	

Requirements: M.D. abrasion loss \leq 30,00 %

Results:

- Acceptable value
- Material accepted